

REACTIVE DYES
for dyeing cellulosic fibres
SCHECOTON



Ø ZDHC






www.guzide.com.tr

SCHECOTON REACTIVE DYES


100% COTTON AT 60°C	 GUZIDE Product	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY		
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS X=12		EXHAUST DYEING	CONTINUOUS DYEING	COLD PAD BATCH
								WET	DRY			
	SCHECOTON YELLOW MC	2%	M	110	F	4-5	4-5	4	4-5	+		+
	SCHECOTON EXTRA YELLOW CB	2%	M	100	F	3	4-5	4-5	4	+	+	+
	SCHECOTON YELLOW 3RS 150%	2%	M	60	F	3-4	4	3-4	4	+	+	+
	SCHECOTON BRILL. YELLOW 3GL	2%	M	110	G	4-5	4-5	4	4-5	+	+	+
	SCHECOTON ORANGE MC	2%	M	100	P	4-5	3-4	4	4	+		+
	SCHECOTON EXTRA ORANGE CB	2%	M	100	G	3	4-5	3-4	4-5	+	+	+
	SCHECOTON DARK ORANGE 4R	2%	H	100	G	3-4	4	4	4	+	+	+
	SCHECOTON RED MC	2%	M	100	F	4-5	4-5	4	5	+		+
	SCHECOTON RED RB	2%	M	100	G	4	4-5	4	4	+	+	+
	SCHECOTON EXTRA RED CB	2%	M	100	F	4	4	4	4	+	-	+
	SCHECOTON BRILL. RED 3BS 150%	2%	M	100	F	4	4-5	4	4-5	+	+	+
	SCHECOTON ROSE 3B	2%	M	100	F	4	4-5	4	4-5	+	+	+
	SCHECOTON EXTRA CARMINE CB	2%	M	100	G	4	4	3-4	4-5	+	+	+

SCHECOTON REACTIVE DYES

100% COTTON AT 60°C	 GUZIDE Product	% OF SHADE	GENERAL PROPERTIES			FASTNESS PROPERTIES				SUITABILITY		
			AFFINITY	SOLUBILITY (PLAIN WATER)	DISCHARGEABILITY	LIGHT FASTNESS (ISO 105-B02)	WASHING FASTNESS (ISO 105 C06)	RUBBING FASTNESS X=12		EXHAUST DYEING	CONTINUOUS DYEING	COLD PAD BATCH
								WET	DRY			
	SCHECOTON OCEAN BLUE S	2%	H	100	P	4-5	4	4-5	4	+	+	+
	SCHECOTON TURQ. BLUE G 266%	2%	M	65	P	3-4	3-4	3-4	4	+	+	+
	SCHECOTON BLUE MC	2%	M	100	G	4-5	4	3-4	4-5	+		+
	SCHECOTON BLUE BRF	2%	H	100	F	5	4	4-5	4	+	+	+
	SCHECOTON BRILL. BLUE R Spec. 160%	2%	M	80	P	4-5	4-5	5	4-5	+	+	+
	SCHECOTON NAVY CB	2%	M	100	G	3-4	4	3	4	+	+	+
	SCHECOTON NAVY BLUE CB	2%	M	100	G	3-4	4-5	3-4	4-5	+	+	+
	SCHECOTON MIDNIGHT S	6%	M	130	G	4	4-5	3-4	4-5	+	+	+
	SCHECOTON BLACK B 133%	6%	M	130	G	4	4-5	3-4	4-5	+	+	+
	SCHECOTON BLACK NN	6%	H	100	G	4	4-5	4	4-5	+	+	+
	SCHECOTON BLACK DSR	6%	H	100	G	4	4-5	4	4-5	+	+	+
	SCHECOTON SUPER BLACK R	6%	H	100	G	4	4-5	4	4-5	+	+	+
	SCHECOTON SUPER BLACK G	6%	H	100	G	4	4-5	4	4-5	+	+	+

Our Quality Policy :-

- TARGETING CUSTOMER SATISFACTION
- MEETING CUSTOMER NEEDS ON TIME
- LEAD OUR EMPLOYEES TO GOALS, KNOW THEM AND PROVIDES THE CONTINUITY OF TRAININGS THAT ENABLE A CHANGE OF BEHAVIOR
- TO BE A COMPANY THAT COMPLIES WITH THE CONDITIONS OF QUALITY MANAGEMENT
- CONTINUOUSLY REVIEW AND IMPROVE ITS EFFECTIVENESS, AND MEETS LEGAL AND APPLICABLE REQUIREMENTS IN ACCORDANCE WITH CUSTOMER AND RELATED PARTIES 'DEMANDS'



GÜZİDE
Mağazası Tekstil Kimyasalları
San. ve Tic. Ltd. Şti.

Narlıkapı Cad. No: 68 / A Samatya / Fatih / İSTANBUL

Telefon : +90 212 530 99 55
Fax : +90 212 586 27 27
E-Posta : info@guzide.com.tr
Url : www.guzide.com.tr